



SECTION 09 7505

ULTRACOMPACT WALL FINISHES - THICK SET

PART 1. GENERAL

1.1 SUMMARY

A. Section Includes:

1. Ultracompact interior wall finishes.
2. Setting materials and accessories

B. Related Sections:

1. Division 01: Administrative, procedural, and temporary work requirements.
2. Section [] - Cementitious backer unit substrate.
3. Section [] - Gypsum board substrate.

1.2 REFERENCES

A. American National Standards Institute (ANSI):

1. A108.1B - Installation of Ceramic Tile on a Cured Portland Cement Mortar Setting Bed with Dry-Set or Latex Portland Cement Mortar.
2. A108.10 - Installation of Grout in Tilework.
3. A118.4 - Latex-Portland Cement Mortar.
4. A118.6 - Ceramic Tile Grouts.

B. ASTM International (ASTM):

1. C97/C97M - Standard Test Methods for Absorption and Bulk Specific Gravity of Dimension Stone.
2. C99/C99M - Standard Test Method for Modulus of Rupture of Dimension Stone.
3. C170/C170M - Standard Test Method for Compressive Strength of Dimension Stone.
4. C370 - Standard Test Method for Moisture Expansion of Fired Whiteware Products.
5. C373/C373M - Standard Test Method for Water Absorption, Bulk Density, Apparent Porosity, and Apparent Specific Gravity of Fired Whiteware Products.
6. C482 - Standard Test Method for Bond Strength of Ceramic Tile to Portland Cement Paste.
7. C484 - Standard Test Method for Thermal Shock Resistance of Glazed Ceramic Tile.
8. C501 - Standard Test Method for Relative Resistance to Wear of Unglazed Ceramic Tile by the Taber Abraser.
9. C648 - Standard Test Method for Breaking Strength of Ceramic Tile.
10. C650 - Standard Test Method for Resistance of Ceramic Tile to Chemical Substances.
11. C674 - Standard Test Method for Flexural Properties of Ceramic Whiteware Materials.
12. C880/C880M - Standard Test Method for Flexural Strength of Dimension Stone.
13. C1028 - Standard Test Method for Determining the Static Coefficient of Friction of Ceramic Tile and Other Like Surfaces by the Horizontal Dynamometer Pull-Meter Method.
14. C1353/C1353M - Standard Test Method for Abrasion Resistance of Dimension Stone Subjected to Foot Traffic Using a Rotary Platform, Double-Head Abraser.

C. Greenguard Environmental Institute (GEI) - Certification Programs.

1.3 SUBMITTALS

A. Submittals for Review:

1. Samples:

- a. [3 x 3] [] x [] inch ultracompact sheet samples [in specified color.] [showing available colors.]
- b. [3/8 x 3/8 x 3] [] x [] x [] inch grout samples [in specified color.] [showing available colors.]
- c. [3] [] inch long joint sealer samples [in specified color.] [showing available colors.]

B. Sustainable Design Submittals:

1. Recycled Content: Certify percentages of post-consumer and pre-consumer recycled content.
2. Low-Emitting Materials: Certify volatile organic compound (VOC) content.



COSENTINO®

imagine & anticipate

SECTION 09 7505

ULTRACOMPACT WALL FINISHES - THICK SET

C. Closeout Submittals:

1. Maintenance Data: Include recommended cleaning materials and procedures, and list of materials detrimental to ultracompact sheet.

COSENTINO CENTRAL

Ctra. Baza - Huércal Overa, Km. 59 - 04850 Cantoria - Almería (España) Tel.

(+34) 950 444 175 - Fax (+34) 950 444 226



Silestone Quartz
Dekton Ultracompact
Sopos Granite



SECTION 09 7505

ULTRACOMPACT WALL FINISHES - THICK SET

1.4 QUALITY ASSURANCE

A. Manufacturer Qualifications:

1. Minimum [10] [] years [documented] experience in manufacture of solid surfacing materials.
2. Current USGBC Environmental Management System Certificate holder.

B. Mockup:

1. Construct wall finish mockup, [6] [] feet wide x [6] [] feet high.
2. Locate [where directed.] [].
3. Approved mockup may remain as part of the Work.

1.5 WARRANTY

- A. Provide manufacturer's 10 year warranty against defects in materials and workmanship.

PART 2. PRODUCTS

2.1 MANUFACTURERS

- A. Contract Documents are based on products by Cosentino USA, Inc. (www.dekton.com)
- B. Substitutions: [Under provisions of Division 01.] [Not permitted.]

2.2 MATERIALS - ULTRACOMPACT SHEET

A. Ultracompact Surfacing Sheet:

1. Product: Dekton by Cosentino.
2. Composition: Selected raw materials formed into flat slabs utilizing sinterized particle technology.
3. Collection: [Solid.] [Natural.] [Tech.]
4. Color: []. [To be selected from manufacturer's full color range.]
5. Surface finish: [Polished.] [Smooth matte.] [Textured matte.]
6. Thickness: [] mm.
7. Physical characteristics:
 - a. Moisture expansion: 0.02 percent average, tested to ASTM C370.
 - b. Breaking strength: 3963 lbf average, tested to ASTM C648.
 - c. Flexural strength: 10,828 psi average, tested to ASTM C674.
 - d. Water absorption: 0.03 percent average, tested to ASTM C373/C373M.
 - e. Static coefficient of friction (slip resistance): 0.80 dry and 0.66 wet, tested to ASTM C1028.
 - f. Wet dynamic coefficient of friction (DCOF): 0.57 average, tested to ANSI A137.1.
 - g. Resistance to wear: 182.2 average wear index, tested to ASTM C501.
 - h. Thermal shock resistance: No defects, tested to ASTM C484.
 - i. Bond strength: 423 psi average, tested to ASTM C482.
 - j. Specific absorption and gravity, tested to ASTM C97/C97M:
 - 1) Average percent of absorption per weight: 0.02 percent.
 - 2) Average density: 156 pounds per cubic foot.
 - k. Breaking module, tested to ASTM C99/C99M:
 - 1) Average dry breaking strength: 8128 PSI.
 - 2) Average wet breaking strength: 7490 PSI.
 - l. Flexural strength, tested to ASTM C880:
 - 1) Average dry flexural strength: 6840 PSI.
 - 2) Average wet flexural strength: 6205 PSI.
 - m. Resistance to compression, tested to ASTM C170/C170M:
 - 1) Average dry compression: 34,409 PSI.
 - 2) Average wet compression: 17,823 PSI.



COSENTINO®

imagine & anticipate

SECTION 09 7505

ULTRACOMPACT WALL FINISHES - THICK SET

n. Resistance to abrasion, tested to ASTM C1353/C1353M: 349 average abrasion index.

o. Resistance to chemical substances; tested to ASTM C650:

- 1) Acetic acid, 3 percent: No affect.
- 2) Acetic acid, 10 percent: No affect.

COSENTINO CENTRAL

Ctra. Baza - Huércal Overa, Km. 59 - 04850 Cantoria - Almería (España) Tel.

(+34) 950 444 175 - Fax (+34) 950 444 226



Silestone Quartz
Dekton Ultracompact
Sopos Granite

SECTION 09 7505

ULTRACOMPACT WALL FINISHES - THICK SET

- 3) Ammonium chloride, 100 g/L: No affect.
- 4) Citric acid solution, 30 g/L n: No affect.
- 5) Citric acid solution 100 g/L: No affect.
- 6) Lactic acid, 5 percent: No affect.
- 7) Phosphoric acid, 3 percent: No affect.
- 8) Phosphoric acid, 10 percent: No affect.
- 9) Sulphuric acid, 30 g/L: No affect.
- 10) Sulphuric acid, 100 G/L: No affect.
- 11) Chemical pool products: No affect.
- 12) Sodium hydrochlorite solution, 20 mg/L: No affect.
- 13) Hydrochloric acid solution, 3 percent: No affect.
- 14) Hydrochloric acid solution, 18 percent: No affect.
- 15) Potassium hydroxide, 30 g/L: No affect.
- 16) Potassium hydroxide, 100 g/L: No affect.

8. Certifications:

- a. GEI Greenguard Certified.
- b. GEI Greenguard Gold Certified.

2.3 MATERIALS - MORTAR

A. Portland Cement Mortar:

1. Cement: ASTM C150, Type 1, white color.
2. Sand: ASTM C144.
3. Lime: ASTM C207, Type S, hydrated.

B. Latex-Portland Cement Mortar: Ultraflex LFT, Ultraflex LFT Rapid, Ultraflex 3, or Kerset mixed with undiluted Keraply by Mapei.

***** OR *****

C. Latex-Portland Cement Mortar: ANSI A118.4.

2.4 MATERIALS - GROUT

A. Grout:

1. Keracolor [S] [U] [Sanded] [Unsanded] Grout by Mapei.
2. Color: [.] [To be selected from manufacturer's full color range.]

***** OR *****

B. Grout:

1. ANSI A118.6, [sanded.] [unsanded.]
2. Color: []. [To be selected from manufacturer's full color range.]

2.5 ACCESSORIES

A. Joint Sealer:

1. Mapesil 100 Percent Silicone Sealant by Mapei.
2. Volatile organic compound (VOC) content: Maximum [50] [] grams per liter.
3. Color: [] [To be selected from manufacturer's full color range.]

2.6 FABRICATION

- A. Cut panels accurately to required shapes and dimensions.**



COSENTINO®

imagine & anticipate

SECTION 09 7505

ULTRACOMPACT WALL FINISHES - THICK SET

B. Fabricate with $[\frac{3}{8}]$ inch joints.

C. Cut flooring to fit at perimeter and around penetrations with maximum $[\frac{1}{4}]$ inch gaps.

COSENTINO CENTRAL

Ctra. Baza - Huércal Overa, Km. 59 - 04850 Cantoria - Almería (España) Tel.

(+34) 950 444 175 - Fax (+34) 950 444 226



Silestone Quartz
Dekton Ultracompact
Sopos Granite



SECTION 09 7505

ULTRACOMPACT WALL FINISHES - THICK SET

PART 3. EXECUTION

3.1 PREPARATION

- A. Clean surfaces to receive panels; remove loose and foreign matter than could interfere with adhesion.
- B. Remove ridges and projections. Fill voids and depressions with patching compound compatible with setting materials.
- C. Allowable Substrate Tolerances: Maximum 1/4 inch in 10 feet variation in substrate surface.

3.2 INSTALLATION

- A. Install panels in accordance with manufacturer's instructions.
- B. Set flooring in thick set mortar bed in accordance with ANSI A108.1.
- C. Install with [hairline] [[3/8] [__]] inch joints.
- D. Allow mortar to set for a minimum of 24 hours.
- E. Grout joints in accordance with ANSI A108.10; finish smooth and flush.
- **** OR ****
- F. Apply joint sealer to joints; finish smooth and flush.
- G. Provide control joints at changes in plane, changes in backup material, at joints between panels and adjacent construction, over joints in substrate, and at maximum [__] feet on center. Fill with joint sealer; finish flush and smooth.

3.3 INSTALLATION TOLERANCES

- A. Maximum variation from level and plumb: 1/4 inch in 10 feet, noncumulative.
- B. Maximum variation in plane between adjacent pieces at joint: Plus or minus 1/16 inch.
- C. Maximum variation in joint width: Plus or minus 1/16 inch.

3.4 CLEANING

- A. Clean panels in accordance with manufacturer's instructions.

END OF SECTION